

Bridge StrengtheningSika® CarboDur® Composite Systems



System Solutions for reinforced and prestressed Concrete, Timber, Steel and Masonry Arch Bridges

Reasons for Strengthening

- Corrosion of the reinforcement
- **■** Corrosion of prestressing cables
- Increased traffic loads
- Inadequate design
- **■** Modified standards/codes
- **■** Excessive cracking of concrete
- Seismic retrofitting

Materials used


FRP Fabrics


Uni- and/or bidirectional fabrics with carbon, glass and aramid fibers. Mostly used for seismic retrofitting and shear strengthening.

CFRP Plates

Carbon fibre plates produced by pultrusion process with precise material properties. Mostly used for flexural and shear strengthening of dynamic loaded structures such as bridges, etc.

Cover Pictures: Prestressed concrete bridge Sika® «World record» in composite-plate length, Australia Steel-concrete bridge Sika® «Tailor made» Compositeplate, United Kingdom






Sika® Systems

Flexural Strengthening with


- Sika® CarboDur® CFRP plates Sika® CarboHeater, heating device for rapid application
- Sika® CarboDur® prestressed **CFRP** plates
- SikaWrap® FRP fabrics



Sika® CarboDur®

Shear Strengthening with

- Sika® CarboShear® L CFRP plates
- SikaWrap® FRP fabrics




Seismic Retrofitting with ■ SikaWrap® FRP fabrics



All Sika® Composite materials are bonded with Sikadur® High strength epoxy adhesives

Shear Strenghening





Flexural Strengthening









Seismic Retrofitting





Timber and Steel Bridges





Prestressed Strengthening







Bridge StrengtheningSika® CarboDur® Composite Systems

System Components

OFFIN PLATE OF ALCOHOLOGIC						
CFRP Plates System Cor	nponents					
Sika [®] CarboDur [®]		Type S	Type M	Type H		
CFRP plates	Elastic modulus	165 000 N/mm ²	210 000 N/mm ²	300 000 N/mm ²		
	Tensile strength	2800 N/mm ²	2800 N/mm ²	1350 N/mm ²		
Sika® Prestressing	Prestressing of Sika® CarboDur® plates over 200 kN (20 tons) with Sika® StressHead or					
Systems	Sika® LEOBA CarboDur® prestressing system					
Sika® CarboHeater	Fast application (2 – 3 hrs) of Sika® CarboDur® plates					
Heating device						
Sika [®] CarboShear [®] L	Min. tensile load	126 kN/40 mm width				
L-shaped CFRP plates	Elastic modulus	120 000 N/mm ²				
Sikadur®		Sikadur [®] -30	Sikadur ^e 30 LP	Sikadur ^e -41		
Epoxy adhesives	Application temperature	10 − 35 °C	25 − 55 °C	10 − 35 °C		
and mortars	Elastic modulus	12 800 N/mm ²	10 000 N/mm ²	9 000 N/mm ²		
	Bond strength	> 4 N/mm ²	> 4 N/mm²	> 4 N/mm ²		
		(concrete failure)	(concrete failure)	(concrete failure)		
	Use	Plate adhesive	Plate adhesive	Repair mortar		
Sika° CarboHeater Heating device Sika° CarboShear° L L-shaped CFRP plates Sikadur° Epoxy adhesives	Fast application (2 – 3 hrs) of some strength of stre	126 kN/40 mm width 120 000 N/mm² Sikadur°-30 10 - 35 °C 12 800 N/mm² > 4 N/mm² (concrete failure)	25 – 55 °C 10 000 N/mm² > 4 N/mm² (concrete failure)	10 – 35 °C 9000 N/mm² > 4 N/mm² (concrete failure)		

Fabrics System Components

rabilità d'accom compa	,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,			
SikaWrap®	Several types of SikaWrap® FRP fabrics are available to meet the requirement of specifier and contractor. Unidirectional woven and non-			
FRP Fabrics	woven fabrics made of glass, aramid and different types of carbon fibers are available. Bi-directional types can be offered with carbon			
	and glass fibers. The range of areal weight is between 200 and 600 g/m² for carbon, 400 to 1000 g/m² for glass and 300 to 600 g/m² for			
	aramid fiber fabrics. Further possibilities and fiber combinations are available on request.			
Sikadur®	All SikaWrap® fabrics can be impregnated with the system tested Sikadur® impregnating resins that are all suited for the most			
Epoxy impregnating resins	common substrate types. are all suited for the most common substrate types.			

For additional information see corresponding Product Data Sheets.

Test Reports

Fatigue and Failure Test	EMPA Test Report	1999
Test beams B1 and B2	No. 402017E/2	
Sika CarboDur Structural Strengthening	EMPA Test Report	2001
System, Fatigue and Failure Test, Test beam B3	No. 415053E/3	
Sika CarboDur Structural Strengthening System,	EMPA Test Report	1999
Bonding of CFRP strips under dynamic load	No. 170569e-1	
Bonding of CarboDur CFRP plates under	EMPA Test Report	2001
dynamic load	No. 418931E	

Approvals

General construction approval for steel plate	German Institute	
strengthening with Sikadur®-30	of Construction	07.04.95
and Icosit® 277	No. 7-36.1-30, Germany	
General construction approval for	German Institute	
Sika® CarboDur®, Plates Typ S	of Construction	11.11.97
	No. 7-36.12-29, Germany	
Report/Technical Investigation for CarboDur®,	SOCOTEC	07.08.00
Plates Typ S and SikaWrap®-230C fabric	No. HX0823, France	
Evaluation Report for SikaWrap ® FRP Systems	ICBO No. ER-5558,	01.04.00
	California II C	

Also available from Sika















Sika Services AG

Corporate Construction
CH-8048 Zürich
Switzerland
Phone +41 44 436 40 40
Fax +41 44 436 46 86
www.sika-construction.com

Your local Sika Company

Our most current General Sales Conditions shall apply. Please consult the Product Data Sheet prior to any use and processing.







