

PRODUCT DATA SHEET

Sikadur[®]-300

2-COMPONENT EPOXY IMPREGNATION RESIN

DESCRIPTION

Sikadur[®]-300 is a 2-component, epoxy based impregnating resin.

USES

Sikadur[®]-300 may only be used by experienced professionals.

Sikadur[®]-300 is used as

- Impregnating resin for SikaWrap[®] fabric reinforcement for the wet application method
- Primer resin for the wet application system

CHARACTERISTICS / ADVANTAGES

- Easy mix and application by trowel and impregnation roller
- Manufactured for manual or mechanical saturation methods
- Good adhesion to many substrates
- High mechanical properties
- Extra-long pot life

APPROVALS / CERTIFICATES

- Road and Bridges Research Institute (Poland): IBDiM No AT/2008-03-336/1.
- Adhesive for structural bonding tested according to EN 1504-4, provided with the CE-mark

PRODUCT INFORMATION

Composition	Epoxy resin	
Packaging	Component A:	22.305 kg
	Component B:	7.695 kg pails
Colour	Component A:	light-yellow to amber liquid
	Component B:	pale yellow to clear liquid
	Components A + B mixed:	light-yellow to clear liquid
Shelf life	24 months from date of production	
Storage conditions	Store in original, unopened, sealed and undamaged packaging in dry conditions at temperatures between +5 °C and +30 °C. Protect from direct sunlight.	
Density	Component A+B mixed (at +23 °C)	1.16 kg/L
Viscosity	Shear rate: 50 /s	
	Temperature	Viscosity
	+15 °C	~2 000 mPas
	+23 °C	~700 mPas
	+40 °C	~200 mPas

TECHNICAL INFORMATION

Modulus of Elasticity in Flexure	7 days (at +23 °C)	~2 800 N/mm ²	(DIN EN 1465)
Tensile Strength	7 days (at +23 °C)	~45 N/mm ²	(ISO 527)
Modulus of Elasticity in Tension	7 days (at +23 °C)	~3 500 N/mm ²	(ISO 527)
Elongation at Break	7 days (at +23 °C)	1.5 %	(ISO 527)
Tensile Adhesion Strength	Concrete fracture on sand-blasted substrate	> 2 N/mm ²	(EN ISO 4624)
Coefficient of Thermal Expansion	Temperature range -20 °C – +40 °C	6.0 x 10 ⁻⁵ per °C	(EN 1770)
Glass Transition Temperature	Curing time 30 days	Curing temperature +30 °C	TG +53 °C (EN 12614)
Heat Deflection Temperature	Curing time 7 days 7 days 3 days 7 days	Curing temperature +15 °C +23 °C +40 °C +40 °C	HDT +43 °C +49 °C +60 °C +66 °C (ASTM D 648)
	Resistant to continuous exposure +45 °C.		
Service Temperature	-40 °C to +45 °C		

SYSTEMS

System Structure	Substrate primer - Sikadur®-330 / Sikadur®-300. Impregnating/laminating resin - Sikadur®-300. Structural strengthening fabric - SikaWrap® type to suit requirements.
-------------------------	--

APPLICATION INFORMATION

Mixing Ratio	Component A : component B = 100 : 34.5 by weight When using bulk material the exact mixing ratio must be safeguarded by accurately weighing and dosing each component.		
Consumption	See the "Method Statement for SikaWrap® manual wet application" Ref 850 41 03 and the "Method Statement for SikaWrap® saturator machine wet application" Ref 850 41 04. Guide: 0.4–1.0 kg/m ² .		
Ambient Air Temperature	+15 °C min. / +40 °C max.		
Dew Point	Beware of condensation. Substrate temperature during application must be at least 3 °C above dew point.		
Substrate Temperature	+15 °C min. / +40 °C max.		
Substrate Moisture Content	< 4 % pbw		
Pot Life	Temperature +15 °C +23 °C +40 °C	Potlife ~6 hours ~4 hours ~90 minutes	Open time ~3 hours – ~60 minutes (EN ISO 9514)

The potlife begins when the resin and hardener are mixed. It is shorter at high temperatures and longer at low temperatures. The greater the quantity mixed, the shorter the potlife. To obtain longer workability at high temperatures, the mixed adhesive may be divided into portions. Another method is to chill components A+B before mixing them (not below +5 °C).

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

The substrate must be sound and of sufficient tensile strength to provide a minimum pull off strength of 1.0 N/mm² or as per the requirements of the design specification.

See also the "Method Statement for SikaWrap® manual wet application" Ref 850 41 03 and the "Method Statement for SikaWrap® saturator machine wet application" Ref 850 41 04.

SUBSTRATE PREPARATION

See the "Method Statement for SikaWrap® manual wet application" Ref 850 41 03 and the "Method Statement for SikaWrap® saturator machine wet application" Ref 850 41 04.

MIXING

Pre-batched units:

Mix components A+B together for at least 3 minutes at low speed. Avoid aeration while mixing. Then, pour the whole mix into a clean container and stir again for approx. 1 more minute at low speed to keep air entrapment at a minimum.

Bulk packing, not pre-batched:

Add the components in the correct proportions into a suitable mixing pail and stir correctly using an electric low speed mixer as above for pre-batched units.

APPLICATION METHOD / TOOLS

See the "Method Statement for SikaWrap® manual wet application" Ref 850 41 03 and the "Method Statement for SikaWrap® saturator machine wet application" Ref 850 41 04.

CLEANING OF EQUIPMENT

Clean all equipment immediately with Sika® Colma Cleaner. Cured material can only be removed mechanically.

IMPORTANT CONSIDERATIONS

This product may only be used by experienced professionals.

Sikadur®-300 must be protected from rain for at least 24 hours after application. Ensure placement of fabric and laminating with roller takes place within open time.

For application in cold or hot conditions, pre-condition material for 24 hours in temperature controlled storage facilities to improve mixing, application and pot life limits.

For further information on over coating, number of layers or creep, please consult a structural engineer for calculations and see also the "Method Statement for SikaWrap® manual wet application" Ref 850 41 03 and the "Method Statement for SikaWrap® saturator machine wet application" Ref 850 41 04.

Sikadur® resins are formulated to have low creep under permanent loading. However due to the creep behaviour of all polymer materials under load, the long term structural design load must account for creep. Generally the long term structural design load must be lower than 20-25% of the failure load. Please consult a structural engineer for load calculations for your specific application.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PT. Sika Indonesia Head Office and

Jl. Raya Cibinong-Bekasi Km.20
Limusnunggal-Cileungsi
Bogor 16820-Indonesia
Tel. +62 21 8230025, Fax +62 21 8230026
Web: idn.sika.com
Email: sikacare@id.sika.com



Product Data Sheet
Sikadur®-300
September 2016, Version 02.01
020206040010000006

Sikadur-300-en-ID-(09-2016)-2-1.pdf

