

BUILDING TRUST

PRODUCT DATA SHEET

Sika® Plastiment® VZ

WATER REDUCING AND SET RETARDING

DESCRIPTION

A liquid concrete plasticizer and water reducing agent with set retarding effect.

USES

Sika® Plastiment® VZ is used as a general purpose admixture where the placing conditions for high quality concrete are more demanding such as:

- Elevated temperatures.
- Fair faced concrete.
- Pumped concrete.
- Ready mix concrete.
- Areas where large volumes must be placed at one time.
- High mechanical strengths are required.

FEATURES

Sika® Plastiment® VZ provides the following properties:

- Increased setting time in hot weather. Accelerated hardening after setting.
- Improved workability without increase water content.
- Reduced water without loss of workability.
- Increased strengths.
- Reduced shrinkage and creep.
- Long lasting control of slump loss.
- Better surface finish.
- Chloride free does not attack reinforcement.

PRODUCT INFORMATION

Composition	Polyhydroxy Carbon Salts.
Packaging	240 kg Drum 1 180 kg IBC's or Bulk delivery
Shelf life	12 months from date of production if stored properly in undamaged un- opened, original sealed packaging
Storage conditions	Store in dry conditions at temperatures between +5 $^{\circ}$ C and +35 $^{\circ}$ C. Protect from direct sunlight and frost.
Appearance and colour	Liquid / Clear up to turbid yellowish liquid

APPLICATION INFORMATION

Recommended dosage

0.15 % - 0.40 % by weight of cement

The effective dosage of Sika® Plastiment® VZ depends on the type of cement and fine aggregate, in general dosage of Sika® Plastiment® VZ is in the range of 0.15 % - 0.25 % for concrete having low absorption fine aggregate.

The dosage rate can be increased to 0.60 % to overcome difficulties in quality of cement and aggregates, high temperature and difficult placing

Product Data Sheet Sika® Plastiment® VZ February 2024, Version 01.03 021303011000000045

	conditions. Concrete trial mix shall be carried out to confirm the effective dosage and its effect to concrete properties
Compatibility	Sika® Plastiment® VZ is compatible with all types of Portland cement including S.R.C.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

DISPENSING

Sika® Plastiment® VZ should be dispensed directly into the mixing water prior to its addition to the aggregates.

When accidental overdosing occurs, Sika® Plastiment® VZ does not entrain excessive amounts of air, however the set retarding effect increases. During this period the concrete must be kept moist in order to prevent premature drying out.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PT. Sika Indonesia Head Office and Manufacturing

Jl. Raya Cibinong-Bekasi Km.20 Limusnunggal-Cileungsi Bogor 16820-Indonesia Tel. +62 21 8230025, Fax +62 21 8230026





Product Data Sheet Sika® Plastiment® VZ February 2024, Version 01.03 021303011000000045



