

## PRODUCT DATA SHEET

# SikaShield® P24 MG 3 mm

Plastomeric bituminous membrane surfaced with mineral granules and flexible at 0 °C

### DESCRIPTION

SikaShield® P24 MG 3 mm is an APP modified bituminous roof waterproofing membrane with a thickness of 3 mm. It is reinforced with a non-woven polyester fabric and is flexible at 0 °C. The top surface is coated with mineral granules, which allows the permanent exposure to UV radiation. The underside of the product has a burn-off film for easy torch-application.

### USES

The Product is used as a waterproofing membrane for:

- Balconies and terraces
- Flat or sloping roofs with up to 15 % gradient

The Product is used as a:

- Exposed cap sheet in a multi-layer system

### FEATURES

- Decorative mineral granules
- Easy to install by torching method
- Fully bonded
- Flexible in cold temperatures
- Good mechanical properties (tensile, tear, shear)
- Can be painted immediately after application
- Tiles can be placed directly onto the membrane

### PRODUCT INFORMATION

<b>Packaging</b>	Roll width	1.0 m	(EN 1848-1)
	Roll length	10.0 m	

Refer to current price list for packaging variations.

<b>Shelf life</b>	12 months from date of production
-------------------	-----------------------------------

<b>Storage conditions</b>	The Product must be stored in original unopened and undamaged packaging in dry conditions and temperatures between +5 °C and +35 °C. Store in a vertical position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to packaging.
---------------------------	----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

Appearance and colour	Top surface	Mineral Granules
	Bottom surface	Polyethylene film
	Top layer colour	Refer to current price list for color variations
Effective thickness	Effective thickness	3.0 mm ± 0.2 mm (EN 1849-1)

## TECHNICAL INFORMATION

Maximum tensile force	Longitudinal (MD)	600 N/50 mm ± 120 N/50 mm	(EN 12311-1)
	Transversal (CMD)	400 N/50 mm ± 80 N/50 mm	
Elongation at maximum tensile force	Longitudinal (MD)	35% ± 20%	(EN 12311-1)
	Transversal (CMD)	40% ± 20%	
Resistance to tear	Longitudinal (MD)	150 N ± 45 N	(EN 12310-1)
	Transversal (CMD)	150 N ± 45 N	
Joint shear resistance	Longitudinal	500 N/50 mm ± 100 N/50 mm	(EN 12317-1)
	Transversal	350 N/50 mm ± 70 N/50 mm	
Flexibility at low temperature	≤ 0 °C		(EN 1109)
Watertightness	Method B: 24 hours at 60 kPa	Pass	(EN 1928)

## APPLICATION INFORMATION

Ambient air temperature	Minimum	+5 °C
	Maximum	+40 °C
Relative air humidity	Maximum	80 %
Substrate temperature	Minimum	+5 °C
	Maximum	+40 °C

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER INFORMATION

- Guidelines and good practice for torch-applied membranes
- Method Statement - Roofing Build-up with Bituminous Membranes

## ECOLOGY, HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of

the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w).

# APPLICATION INSTRUCTIONS

## SUBSTRATE QUALITY

### SYSTEM DESIGN

Consider the following when designing the roof system:

- The supporting structure must be of sufficient structural strength to support all new and existing layers of the roof build-up.
- The complete roof system must be designed to withstand and be secured against wind uplift loadings.
- The wind uplift resistance of the adhered roofing assembly is limited by the adhesion strength of the Product to the substrate.

### SUBSTRATE CONDITION

The substrate surface must be uniform, firm, smooth and free of any sharp protrusion or burrs, clean, dry, free of grease, laitance, oil, dust and loosely adhering particles.

## APPLICATION

### IMPORTANT

#### Unrolling at low temperatures

At low temperatures, the membrane becomes less flexible.

1. Be careful when unrolling to avoid damaging the membrane.

### IMPORTANT

#### Damage through footwear

Footwear with spikes or sharp protrusions may puncture the membrane.

1. Use footwear with a flat profile when walking over the membrane.

### IMPORTANT

#### Damage through overheating

The polyester reinforcement melts at +260 °C. If it is damaged through overheating, the membrane becomes unusable.

1. Keep moving the flame while torching to avoid overheating the membrane.

### IMPORTANT

#### Reduced adhesion through insufficient heating

Make sure to heat the membrane sufficiently. If it is not sufficiently heated, the adhesion to the substrate, between layers or on the overlaps will be reduced.

1. If the membrane does not adhere to other elements, lift and retorch the unbonded areas.

Note: If a seasonal symbol is printed on the roll's label, it is advisable to use the membrane during the indicated season.

Note: When laying the membrane at high temperatures, the integral adhesive will become 'tacky' and may restrict laying operations.

## ALIGNMENT

### IMPORTANT

#### Avoid coinciding joints

To avoid coinciding joints, lay the membranes parallel to one another. When applying on another bituminous membrane, make sure to straddle the overlaps of the previous layer.

1. Unroll the membrane.
2. Align the membrane.
3. Re-roll the membrane before application.

### MEMBRANE OVERLAPS

1. Overlap the membranes by a minimum of 100 mm on the sides and 150 mm on each end.
2. At the end overlap, cut off a corner measuring 100 mm per side at an angle of 45°.
3. Weld the overlaps with great care until you see a trickle of melted mixture about 10 mm wide coming out along the line of the overlap.

### TORCHING

1. Heat the substrate and the backing film on the underside of the membrane with a gas burner. When the backing film starts to melt, the membrane is ready to stick.
2. Roll the heated membrane forward and press it firmly against the substrate to bond it.
3. Make sure a bead of melted bitumen is visible along the full length of the overlap sides and ends when laying.

#### Suitable substrates for torching

- Concrete
- Perlite screed
- Bituminous membranes with a smooth surface
- Coatings (check the compatibility)
- Brick masonry
- Cementitious screeds

### DETAILING

1. Use a sharp knife to cut in all details such as internal and external corners, upstands, vent pipes, drains, support metalwork etc.

Refer to the relevant method statement for further information on detailing.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### **PT. Sika Indonesia Head Office and Manufacturing**

Jl. Raya Cibinong-Bekasi Km.20  
Limusnunggal-Cileungsi  
Bogor 16820-Indonesia  
Tel. +62 21 8230025, Fax +62 21  
8230026



**Product Data Sheet**  
SikaShield® P24 MG 3 mm  
July 2023, Version 02.01  
020920011990001692

SikaShieldP24MG3mm-en-ID-(07-2023)-2-1.pdf

