

# PRODUCT DATA SHEET

## GIP Panel Render

### RENDER FOR AAC PANEL

#### DESCRIPTION

GIP Panel Render is a one component, pre-packed polymer modified mortar combining cement with selected grades of sand and several admixtures.

#### USES

For finish work on AAC Panel

#### CHARACTERISTICS / ADVANTAGES

- Multi function as plaster and finish coat.
- Excellent adhesion
- Prevents hair cracks caused by material shrinkage
- More efficient, only  $\pm 5$  mm thickness
- Easy to use and apply, just add water

#### PRODUCT INFORMATION

Packaging	25 kg bag
Appearance / Colour	Powder / Grey
Shelf life	9 months from date of production if stored properly in original, unopened and undamaged sealed packaging
Storage conditions	Stored in dry conditions at temperatures between +5 °C and +30 °C
Density	~1.65 kg/L

#### TECHNICAL INFORMATION

Compressive strength	28 days	~6 N/mm <sup>2</sup>	(ASTM C-109)
Tensile adhesion strength	28 days	~0.3 N/mm <sup>2</sup>	(BS EN 1015-12)

#### APPLICATION INFORMATION

Mixing ratio	Water : GIP Panel Render	6.25 – 6.75 L : 25 kg (by weight)
	Water : GIP Panel Render	1 : $\pm 2.7$ (by volume)
	(as per consistency requirement)	
Consumption	~1.25 m <sup>2</sup> per 25 kg bag (based on 5 mm thickness)* *depend on substrate surface profile	
Layer thickness	$\pm 5$ mm	
Ambient air temperature	+8 °C to +40 °C	
Pot Life	~1 h (at +30 °C)	

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY / PRE-TREATMENT

Application area surface must be clean, sound, level and uncontaminated by oil or grease. Remove cement laitance, dust, and loosely adhering particles. Absorbent substrates must be pre-wetted to saturated surface dry (SSD) conditions.

### MIXING

- Pour 6.25 – 6.75 Liter of water into mixing vessel then add 25 kg GIP Panel Render slowly and mix properly.
- Mixing time is ~ 3 minutes. A slow speed mixer is recommended (300 – 600 rpm).

### APPLICATION

- Apply with flat trowel.
- Waiting time before paint application minimum 3 days.

### CLEANING OF EQUIPMENT

Clean all tools and application equipment with water immediately after use. Hardened / cured material can only be mechanically removed.

## IMPORTANT CONSIDERATIONS

Protect the freshly applied product against direct sunlight

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### PT. Sika Indonesia Head Office and Manufacturing

Jl. Raya Cibinong-Bekasi Km.20  
Limusnunggal-Cileungsi  
Bogor 16820-Indonesia  
Tel. +62 21 8230025, Fax +62 21  
8230026



### Product Data Sheet

GIP Panel Render  
August 2020, Version 01.01  
021820101002000018

GIPPanelRender-en-ID-(08-2020)-1-1.pdf