

PRODUCT DATA SHEET

Sika® Poxitar® F

EPOXY-ANTHRACENE OIL-COMBINATION HEAVY DUTY COATING FOR STEEL AND CONCRETE

DESCRIPTION

Resistant 2-pack coating of low solvent content based on an epoxy-anthracene oil-combination with mineral fillers.

Low solvent content according to Protective Coatings Directive of German Paint Industry Association (VdL-RL 04).

USES

Sika® Poxitar® F may only be used by experienced professionals.

Protective coating for concrete and steel, for buried and submerged structures, e.g. sewage systems, chemical industry etc.

Also suitable where application onto damp concrete is inevitable.

Not suitable for surfaces in contact with drinking water, housing, stables etc.

CHARACTERISTICS / ADVANTAGES

After complete curing Sika® Poxitar® F is:

- Tough hard, heavy duty
- Abrasion and impact resistant
- Excellent resistance to water and chemicals

Sika® Poxitar® F can be exposed to water immediately after application. But take into consideration that solvents get into the water which leads to temporary contamination. Immediate exposure to water should therefore only be considered in special cases and after consulting the authorities for the protection of environment.

PRODUCT INFORMATION

Packaging	Sika® Poxitar® F Sika® Thinner S SikaCor® Cleaner	35 kg and 17 kg net. 25 L, 10 L and 3 L 160 L and 25 L
Appearance / Colour	Black, tinted red	
Shelf life	Min. 2 years	
Storage conditions	In originally sealed containers in a cool and dry environment.	
Density	~1.8 kg/L	
Solid content	~87 % by volume ~96 % by weight	

TECHNICAL INFORMATION

Chemical Resistance	Resistant to water, seawater, barnacles, diluted acids and lyes, neutral salts, mineral and fuel oils, grease, detergents etc. Not resistant to exposure to benzene-hydrocarbons and tar oil.
Temperature Resistance	Dry heat up to approx. +100 °C Damp heat and warm water up to approx. +60 °C Short term exposure up to approx. +80 °C Not resistant to warm water at significant differential of temperature gradient!

SYSTEMS

Systems	<u>Concrete:</u> 2 - 3 x Sika® Poxitar® F 1 st coat to be thinned with max. 5 % by weight Sika® Thinner S, 2 nd coat unthinned. <u>Steel:</u> 2 - 3 x Sika® Poxitar® F Preferably alternating colour shades. In case of heavy mechanical exposure priming with SikaCor® Zinc R is recommended.
----------------	---

APPLICATION INFORMATION

Mixing Ratio	Components A : B = 85 : 15 (By weight)									
Thinner	Sika® Thinner S, only thin material where stated. If necessary max. 5 % Sika® Thinner S may be added to adapt the viscosity. In this case an immediate exposure to water is not possible. If necessary the material components can be tempered.									
Consumption	Theoretical material-consumption/coverage without loss for medium dry film thickness of: <table><thead><tr><th>Description</th><th>Dry</th><th>Wet</th></tr></thead><tbody><tr><td>Film thickness</td><td>150 µm</td><td>175 µm</td></tr><tr><td>Consumption</td><td>0.310 kg/m²</td><td>3.25 m²/kg</td></tr></tbody></table>	Description	Dry	Wet	Film thickness	150 µm	175 µm	Consumption	0.310 kg/m ²	3.25 m ² /kg
Description	Dry	Wet								
Film thickness	150 µm	175 µm								
Consumption	0.310 kg/m ²	3.25 m ² /kg								
Product Temperature	Min. + 5 °C									
Relative Air Humidity	Max. 85 %, except the surface temperature is significantly higher than the dew point temperature, it shall be at least 3 K above dew point. Under unfavourable conditions, e.g. influence of high air humidity into the fresh coating, surface damages (brown discolouration) and possibly little alligatoring may occur. However, this will not affect the quality.									
Surface Temperature	Min. +5 °C									
Pot Life	At +20 °C ~1.5 h									

Waiting Time / Overcoating

Waiting time between operations up to max. 150 µm dry film thickness:

	Waiting time (min.)	Waiting time (max.)
At +5 °C after	36 h	96 h
At +10 °C after	30 h	72 h
At +15 °C after	24 h	60 h
At +20 °C after	12 h	48 h
At +25 °C after	8 h	36 h
At +30 °C after	6 h	24 h

If these maximum waiting times cannot be observed, the surface must be activated by sweep blasting to avoid intercoat adhesion problems. Prior to application of the next coat a thorough dedusting is necessary.

Between SikaCor® Zinc R and Sika® Poxitar® F:
24 h at +20 °C (see product data sheet).

Drying time

Final drying time

At +20 °C and good ventilation final curing is achieved after approx. 8 - 10 days.

Curing also takes place at lower temperatures – below +10 °C – but it takes longer.

Curing also takes place under water.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

Concrete:

Solid and gripping, free of cement laitance, dust, loose and friable particles and other contamination. Concrete moisture content max. 8 %. Sweep blasting increases adhesion. This is particularly important in case of underwater exposure. Large holes, holidays and cavities etc. should be levelled up with e.g. Icoment®-520 Mortar or Sika Poxitar® SW Mortar.

SURFACE PREPARATION

Steel:

Blast-cleaning to Sa 2 ½ according to ISO 12944, part 4. Free from dirt, oil and grease. Average roughness depth Rz ≥ 50 microns

MIXING

Stir component A very thoroughly using an electric mixer (start slowly, then increase up to approx. 300 rpm). Add component B carefully and mix both components very thoroughly (including sides and bottom of the container). Mix for at least 3 minutes until a homogeneous mixture is achieved. Fill mixed material into clean container and mix again shortly as described above. During mixing and handling of the materials always wear protective goggles, suitable gloves and other protective clothings.

APPLICATION

The method of application has a major effect on achieving uniform thickness and appearance. Spray application will give the best results. The indicated dry film thickness is easily achieved by airless spray. Adding solvents reduces the sag resistance and the dry film thickness. In case of application by roller or brush, additional applications may become necessary to

achieve the required coating thickness, depending on type of construction, site conditions, colour shade etc. Prior to major coating operations a test application on site may be useful to ensure the selected application method will provide the requested results.

By brush and roller

Airless-spraying:

- Pressure min. 150 bar
- Diameter of hoses min. 8 mm (¾ inch)
- Nozzle size 0.53 - 0.66 mm (0.021 - 0.026 inch)
- Spraying angle 40° - 80°

CLEANING OF EQUIPMENT

SikaCor® Cleaner

FURTHER INFORMATION

CE-MARKING DIN EN 1504-2

The harmonized European Standard EN 1504-2 "Products and systems for the protection and repair of concrete structures – Definitions, requirements, quality, control and evaluation of conformity – Part 2: Surface protection systems for concrete" gives specifications for products and systems based on methods "hydrophobic impregnation", "impregnation" and "coating". For flooring systems not dedicated to protect or reinstate the integrity of a Concrete structure, EN 13813 applies. Products acc. EN 1504-2 used as flooring systems with mechanical loads also must fulfill EN 13813. Further details to CE-marking can be obtained from the technical document "Sika® Produkte und Systeme nach DIN EN 1504-2"

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

GISCODE: RE 3

This coding enables additional information and help with the creation of operating instructions (WINGIS online) to be obtained on the BG Bau service pages (www.gisbau.de).

Skin contact with epoxy resins can lead to allergies!
Avoid direct skin contact at all costs when handling epoxy resins!

For the selection of suitable protective equipment, we have made our information data sheets 7510 'General notes on occupational safety' and 7511 'General notes for wearing protective gloves' available at www.sika.de. In conjunction with this we also recommend the BG Bau service pages for Information regarding the handling of epoxy resins (www.bgbau.de/gisbau/fachthemen/epoxi).

Information on the safe handling of chemical products, as well as the essential physical, safety-related, toxicological and ecological data can be found in the current safety data sheets. Observe all relevant regulations, e.g. the hazardous substances act. Further notes and information data sheets on product safety and disposal can be found on the Internet at www.sika.de.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PT. Sika Indonesia Head Office and

Jl. Raya Cibinong-Bekasi Km.20
Limusnunggal-Cileungsi
Bogor 16820-Indonesia
Tel. +62 21 8230025, Fax +62 21 8230026
Web: idn.sika.com
Email: sikacare@id.sika.com



SikaPoxitarF-en-ID-(11-2016)-1-1.pdf

Product Data Sheet
Sika® Poxitar® F
November 2016, Version 01.01
020602000120000003