

PRODUCT DATA SHEET

SikaCim[®] Latex

Water resistant bonding agent and mortar admixture

DESCRIPTION

SikaCim[®] Latex is a synthetic rubber emulsion that is used as admixture for cementitious bonding bridges and high quality site-mix mortars.

USES

SikaCim[®] Latex is used as bonding agent and site-mix mortar admixture for the following applications:

- Grouts and screeds
- Patch repair mortars
- Masonry mortars
- Renders
- Tile adhesives

FEATURES

The main advantages of SikaCim[®] Latex are:

- Increased adhesion
- Reduced shrinkage and cracking
- Increased abrasion resistance
- Reduced permeability
- Improved workability
- User friendly
- Suitable on most common construction substrates

PRODUCT INFORMATION

Composition	Styrene Butadiene Liquid
Packaging	10 x 900 mL, Tray
Appearance and colour	Liquid / White
Shelf life	12 months from date of production if stored properly in undamaged unopened, original sealed packaging.
Storage conditions	Store in dry conditions at temperatures between +5 °C and +30 °C. Protect from direct sunlight and frost.
Density	1.01 ± 0.01 kg/L

APPLICATION INFORMATION

Recommended dosage	Bonding bridge	SikaCim [®] Latex : Water : Cement = 1 : 1 : 2 - 3 depend on desired consistency
	Mortar	SikaCim [®] Latex : Water = 1 : 1 to 1 : 3 with cement : sand = 1 : 1 to 1 : 3

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

Never use pure SikaCim® Latex or SikaCim® Latex-water mix directly onto the substrate as bonding bridge, always add cement to the mix.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

The substrate shall be thoroughly clean, free from dust, loose material, surface contamination and materials which reduce bond or prevent suction or wetting by cementitious materials. De-laminated, weak, damaged and deteriorated substrate shall be removed by suitable means before application. Rust, scale, dust and other loose and deleterious materials which reduces bond or contributes to corrosion shall be removed.

MIXING

Mix SikaCim® Latex with the correct amount of water to produce a gauging solution. Pour part of the gauging solution into a suitable mixing container. While stirring slowly, add the cement (for bonding bridge) or add the cement - sand mix (for mortar) to the gauging solution and mix thoroughly until a smooth, uniform and lump-free mix is achieved. Within the mixing time add additional gauging solution to adjust to the desired consistency.

APPLICATION METHOD / TOOLS

Bonding Bridge

Thoroughly pre-wet the prepared substrate a recommended 2 hours before application. Keep the surface wet and do not allow to dry. Before application remove excess water e.g. with a clean sponge. The surface shall appear a dark matt appearance without glistening and surface pores and pits shall not contain water. Using a stiff clean brush work the mix vigorously onto the substrate, forming a thin layer filling all unevenness, pits and pores.

Always apply following layer of mortar "wet on wet" onto bonding bridge.

Mortar

Prepare and mix SikaCim® Latex with water, cement and sand as composition

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PT. Sika Indonesia Head Office and Manufacturing

Jl. Raya Cibinong-Bekasi Km.20
Limusnunggal-Cileungsi
Bogor 16820-Indonesia
Tel. +62 21 8230025, Fax +62 21
8230026



Product Data Sheet

SikaCim® Latex
November 2024, Version 04.01
020301010010000172

SikaCimLatex-en-ID-(11-2024)-4-1.pdf