

PRODUCT DATA SHEET

Sika® ViscoCrete®-2250 ACC

HIGH PERFORMANCE SUPERPLASTICISER

DESCRIPTION

Sika® ViscoCrete®-2250 ACC is a third generation superplasticiser for concrete and mortar. It is designed particularly for production concrete that demands high early strength and high ultimate strength.

USES

Sika® ViscoCrete®-2250 ACC is a unique multipurpose superplasticiser that is particularly suitable for the production of precast concrete. Additionally, it provides ultra-high-water reduction, high early strength and excellent flow characteristics.

With its outstanding combination of good workability and early strength development Sika® ViscoCrete® is used for the following:

- A wide range of applications where good early strength development are required.
- Concrete with ultra-high-water reduction.
- High performance concretes.
- Self-Compacting Concrete (SCC).

FEATURES

Sika® ViscoCrete®-2250 ACC is a powerful superplasticiser based on advanced technology which gives the following advantages:

- High water reduction, resulting in high density, high strength and reduced permeability.
- Extended workability in conjunction with subsequent fast strength development.
- Excellent plasticising effect, resulting in improved flow, placing and compaction characteristics.
- Reduced shrinkage during curing and reduced creep when hardened.
- Provides many opportunities for cost improvement e.g.: Cement reduction, More economic mix design, Earlier moulding release, reduction of potential claims etc.

Sika® ViscoCrete®-2250 ACC contains chloride.

PRODUCT INFORMATION

Composition	Modified polycarboxylate in water.
Packaging	200 L drums (non-returnable) 1 000 L bulk on request
Shelf life	12 months from date of production if stored properly in undamaged unopened, original sealed packaging.
Storage conditions	Store in dry conditions at temperatures between +5 °C and +35 °C. Protect from direct sunlight and frost.
Appearance and colour	Liquid / Turbid colorless to yellowish
Total chloride ion content	< 0.1 % w/w

TECHNICAL INFORMATION

Concreting guidance

The standard rules of good concreting practice, concerning production and placing, are to be followed.
Laboratory trials before concreting on site are strongly recommended when using a new mix design or producing new concrete components.
Fresh concrete must be cured properly and as early as possible.

APPLICATION INFORMATION

Recommended dosage

For medium workability:	0.2% - 0.8% by weight of binder
For concrete with high workability, very low water/cement ratio and for Self Compacting Concrete: The dosage can be increased to overcome difficulties in quality of cement and aggregates or other special concrete requirement. Concrete trial shall be carried out to confirm the effective dosage.	1.0% - 2.0% by weight of binder

Compatibility

Sika® ViscoCrete®-2250 ACC may be combined with the following products:

- Sika® Plastiment® P121R
- Sika® Plastiment® VZ
- Sika® Fume
- SikaFibre®

Do not use viscocrete / viscoflow series combined with sikament series. To produce flowing and / or self-compacting concrete, special concrete mix design is required.
Pre-trials are recommended and mandatory if combinations with the above products are required.
Please consult to our Technical Service Department.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

Excessive water addition or overdosing may cause bleeding or segregation.

Frost:

If frozen and / or if precipitation has occurred, Sika® ViscoCrete®-2250 ACC may be used after thawing slowly at room temperature followed by intensive re-mixing.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

DISPENSING

Sika® ViscoCrete®-2250 ACC is added to the gauging water or added with it into the concrete mixer. To take advantage of the high water reduction, a wet mixing time of at least 60 seconds is recommended.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PT. Sika Indonesia Head Office and Manufacturing

Jl. Raya Cibinong-Bekasi Km.20
Limusnunggal-Cileungsi
Bogor 16820-Indonesia
Tel. +62 21 8230025, Fax +62 21
8230026



Product Data Sheet
Sika® ViscoCrete®-2250 ACC
December 2023, Version 03.01
021301011000004551

SikaViscoCrete-2250ACC-en-ID-(12-2023)-3-1.pdf

