

## PRODUCT DATA SHEET

# Sika® Ucrete® TCCS

(formerly Ucrete® TCCS)

Heavy-duty, colour-stable, encapsulation resin for enhanced aesthetics

### DESCRIPTION

Sika® Ucrete® TCCS is a three-part, heavy-duty, fast-cure encapsulation resin. It provides a highly aesthetic, colour-stable, matt sheen finish for the Sika® Ucrete® CS range of flooring systems.

### USES

Sika® Ucrete® TCCS is used as a top coat for Sika® Ucrete® flooring systems.

Please note:

- The Product may only be used by experienced professionals.

### FEATURES

- Expert installation by fully trained and licensed applicators
- Very good resistance to staining from a specific range of chemicals and food industry products
- Very good resistance to UV exposure
- Good yellowing resistance provides long-term colour stability
- Fast curing
- Non-tainting after curing
- Good temperature resistance

### CERTIFICATES AND TEST REPORTS

- Halal Certification Europe (HCE), Sika® Ucrete®, WHFC, Certificate No. 21453-2/1/1/Y1
- Food and Beverage Facilities Suitability, Sika® Ucrete®, HACCP, Test Report No. I-PE-769-SA-2-RG-06b
- Indoor Air Comfort Gold EN 16516, Sika® Ucrete®, eurofins, Certificate No. IACG-321-01-01-2023

### PRODUCT INFORMATION

|                           |  |  |
|---------------------------|--|--|
| <b>Composition</b>        | Acrylic  |  |
| <b>Packaging</b>          | 7.35 kg<br>Refer to the current price list for available packaging variations.   |  |
| <b>Colour</b>             | Cured colour   | Grey, Light Grey, Cream, Yellow, Bright Yellow, Green, Light Green, Green/ Brown, Red, Orange, Blue, Light Blue. |
| <b>Shelf life</b>         | Always refer to the best-before date of the individual packaging.  |  |
| <b>Storage conditions</b> | The Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to the packaging. |  |

Refer to the current Safety Data Sheet for information on safe handling and storage.

## TECHNICAL INFORMATION

**Tensile adhesion strength** > 2.0 N/mm<sup>2</sup> (concrete failure) (EN 1542)

**Chemical resistance** Laboratory-defined resistance to many individual chemicals. Before proceeding, contact Sika Technical Service for specific information.

## APPLICATION INFORMATION

| Consumption | System                | Consumption               | Area                          |
|-------------|-----------------------|---------------------------|-------------------------------|
|             | Sika® Ucrete® CS10    | 0.4–0.6 kg/m <sup>2</sup> | 12–18 m <sup>2</sup> per unit |
|             | Sika® Ucrete® CS10 AS | 0.4–0.6 kg/m <sup>2</sup> | 12–18 m <sup>2</sup> per unit |
|             | Sika® Ucrete® CS20    | 0.7–0.9 kg/m <sup>2</sup> | 8–10 m <sup>2</sup> per unit  |
|             | Slip resistance R13   |                           |                               |
|             | Sika® Ucrete® CS20    | 1.0–1.2 kg/m <sup>2</sup> | 6–7 m <sup>2</sup> per unit   |
|             | Slip resistance R12   |                           |                               |
|             | Sika® Ucrete® CS20 AS | 0.7–0.9 kg/m <sup>2</sup> | 8–10 m <sup>2</sup> per unit  |
|             | Sika® Ucrete® CS30    | 1.0–1.2 kg/m <sup>2</sup> | 6–7 m <sup>2</sup> per unit   |

Note: Consumption data is theoretical and does not allow for any additional material due to surface porosity, surface profile, variations in level, wastage or any other variations. Apply the Product to a test area to calculate the exact consumption for the specific substrate conditions and proposed application equipment.

|                             |         |        |
|-----------------------------|---------|--------|
| <b>Material temperature</b> | Maximum | +22 °C |
|                             | Minimum | +12 °C |

|                                |         |        |
|--------------------------------|---------|--------|
| <b>Ambient air temperature</b> | Maximum | +22 °C |
|                                | Minimum | +12 °C |

**Dew point** Beware of condensation. The substrate and uncured applied product must be at least +3 °C above the dew point to reduce the risk of condensation or blooming on the surface of the applied product. Low temperatures and high humidity conditions increase the probability of blooming.

|                              |         |        |
|------------------------------|---------|--------|
| <b>Substrate temperature</b> | Maximum | +22 °C |
|                              | Minimum | +10°C  |

**Curing time** The floor can be returned to service after 2 hours.  
Note: Times are approximate and will be affected by changing ambient and substrate conditions.

|                                    |         |           |
|------------------------------------|---------|-----------|
| <b>Waiting time to overcoating</b> | Minimum | 2–3 hours |
|                                    | Maximum | 48 hours  |

Note: Times are approximate and will be affected by changing ambient conditions, particularly temperature and relative humidity.

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### APPLICATION

Application must be undertaken by a fully trained and licensed Sika® Ucrete® applicator.

### LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**PT. Sika Indonesia Head Office and Manufacturing**

Jl. Raya Cibinong-Bekasi Km.20  
Limusunggal-Cileungsi  
Bogor 16820-Indonesia  
Tel. +62 21 8230025, Fax +62 21  
8230026



**Product Data Sheet**  
Sika® Ucrete® TCCS  
October 2024, Version 01.01  
02081400000002019

SikaUcreteTCCS-en-ID-(10-2024)-1-1.pdf

