

PRODUCT DATA SHEET

SikaWrap®-301 C

Carbon fibre, unidirectional, high strength fabric with a fibre area density of 304 g/m² designed for dry or wet application

DESCRIPTION

SikaWrap®-301 C is a unidirectional woven carbon fibre fabric. The Product is made of high strength carbon fibres with an area density of 304 g/m². The fabric is designed for installation using the dry or wet application process.

USES

SikaWrap®-301 C may only be used by experienced professionals.

SikaWrap®-301 C is used as a reinforcement fabric for externally bonded structural strengthening systems on concrete, masonry and wooden substrates.

Externally bonded structural strengthening systems are used for:

- Increasing the flexural and shear loading capacity of elements and structures
- Enhancing the load-carrying capacity or ductility of structural members in compression
- Replacing missing steel reinforcement
- Structural upgrading of weak concrete elements or structures
- Improving impact resistance
- Passive strengthening for seismic event protection

Please note:

- A specialist structural engineer must be consulted for any structural strengthening design calculation.

FEATURES

- Improves the service life of a structure
- Manufactured with thermo-welded weft fibres to keep the fabric stable
- Multifunctional fabric for use in many different strengthening applications
- Flexible and accommodating to different surface planes and geometry (such as beams, columns, chimneys, piles, walls, soffits and silos)

- Available in different widths for optimum utilisation
- Low density for minimal additional weight

SUSTAINABILITY

- Contributes towards satisfying Materials and Resources (MR) Credit: Building Product Disclosure and Optimization — Material Ingredients under LEED® v4

CERTIFICATES AND TEST REPORTS

- Certificate of Technical Valuation, CSLLPP, No. 259/2023
- Technical Agreement, CTPC, No. 016-01/488-2022
- Slovakia: Technical Assessment, TSUS, No. SK04-ZSV-2669
- Test Report, Ministry of Regional Development (Ukraine), No. 3HT-219-2167.13-001

PRODUCT INFORMATION

Construction	Fibre orientation	0° (longitudinal, unidirectional)
	Warp (longitudinal)	Black carbon fibre, 99 %
	Weft (transversal)	White thermoplastic heat-set fibre, 1 %
Packaging	Rolls, 500 mm wide	100 m
	Refer to the current price list for available packaging variations.	
Fibre type	Selected high strength carbon fibres	
Shelf life	24 months from date of production	
Storage conditions	The Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +35 °C. Protect the Product from direct sunlight. Always refer to packaging.	
Dry fibre thickness	0.167 mm	
Mass per area	(304 ± 10) g/m ²	
Dry fibre density	1.80 g/cm ³	

TECHNICAL INFORMATION

Dry fibre modulus of elasticity in tension	230 kN/mm ²	(ISO 10618)
Dry fibre tensile strength	4900 N/mm ²	(ISO 10618)
Dry fibre elongation at break	1.7 %	(ISO 10618)
Design nominal thickness	0.167 mm	
Design nominal cross section	167 mm ² per metre width	
Laminate tensile strength	Mean	4100 N/mm ² (EN 2561)
	5 % characteristic	3600 N/mm ²
	Mean	3900 N/mm ² (ASTM D3039)
	Characteristic (ACI 440.2R)	3300 N/mm ²
All values refer to the relevant design nominal thickness.		
Laminate modulus of elasticity in tension	Mean	230 kN/mm ² (EN 2561)
	5 % characteristic	220 kN/mm ²
	Mean	220 kN/mm ² (ASTM D3039)
All values refer to the relevant design nominal thickness.		
Laminate elongation at break in tension	Mean	1.8% (EN 2561)
	5 % characteristic	1.5%
	Mean	1.75 % (ASTM D3039)
	Characteristic (ACI 440.2R)	1.5%

SYSTEM INFORMATION

System structure

The system build-up and configuration as described must be fully complied with and may not be changed.

Concrete substrate adhesive primer Sikadur®-330

Impregnating or laminating resin Sikadur®-330 or Sikadur®-300

Structural strengthening fabric SikaWrap®-301 C

For detailed information on Sikadur®-330 or Sikadur®-300, together with the resin and fabric application details, please refer to the individual Product Data Sheets and the relevant Method Statement.

APPLICATION INFORMATION

Consumption

DRY APPLICATION WITH SIKADUR®-330

First layer, including primer 1.0–1.5 kg/m²

Following layers 0.8 kg/m²

WET APPLICATION WITH SIKADUR®-300, PRIMER SIKADUR®-330

SikaWrap®-301 C

Primer 0.4–0.6 kg/m²

Fabric layers 0.7 kg/m²

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER INFORMATION

Reference must be made to the following Sika® Method Statements:

- 850 41 02 Method Statement SikaWrap® manual dry application
- 850 41 03 Method Statement SikaWrap® manual wet application

ECOLOGY, HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w).

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

Tensile adhesion strength of the substrate must be a minimum of 1.0 N/mm² or as specified in the strengthening design. If necessary, verify this by applying a test area first.

Refer to the relevant SikaWrap® Method Statement for further information.

SUBSTRATE PREPARATION

Clean and prepare concrete to achieve a laitance-free, contaminant-free, open-textured surface.

Refer to the relevant SikaWrap® Method Statement for further information.

APPLICATION

IMPORTANT

Application by trained personnel

The application of this Product must only be carried out by an applicator that is trained or approved by Sika. The applicator must also be experienced in this type of application.

IMPORTANT

Strictly follow installation procedures

Strictly follow installation procedures as defined in Method Statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

IMPORTANT

Do not interchange different system components

SikaWrap® fabrics are coated to ensure maximum bond and durability with the Sikadur® adhesives, impregnating and laminating resins. To maintain and ensure full system compatibility, do not interchange different system components.

1. **IMPORTANT** Never fold the fabric. Cut the fabric with special scissors, a razor knife or a box-cutter knife.
2. Apply the SikaWrap fabric using the wet or dry application process. Refer to the relevant Method Statement for details on either the impregnating or laminating procedure:
 - 850 41 02 Method Statement SikaWrap® manual dry application
 - 850 41 03 Method Statement SikaWrap® manual wet application

OVERCOATING SIKAWRAP® FABRICS

SikaWrap® fabrics can be overcoated with a cementitious overlay or other coatings for aesthetic or protective purposes. The selection of the overcoating system depends on the exposure and project-specific requirements.

For additional protection from UV light in exposed areas, use one of the following:

- Sikagard®-550 W Elastic
- Sikagard®-675 W ElastoColor
- Sikagard®-680 S Betoncolor
- Sikagard®-5500

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PT. Sika Indonesia Head Office and Manufacturing

Jl. Raya Cibinong-Bekasi Km.20
Limusunggal-Cileungsi
Bogor 16820-Indonesia
Tel. +62 21 8230025, Fax +62 21
8230026



Product Data Sheet

SikaWrap®-301 C
January 2024, Version 04.01
020206020010000014

SikaWrap-301C-en-ID-(01-2024)-4-1.pdf